

IJERT

www.ijert.org

ISSN (Online) : 2278 - 0181

International Journal of
**ENGINEERING RESEARCH
&
TECHNOLOGY**

(Paper Hard Copy)

Published By



www.esrsa.org

International Journal of
Engineering Research & Technology

**International Journal of Engineering Research
& Technology (IJERT)**
Published by ESRSA Publications

ESRSA, Engineering and Science Research Support Academy
Publications publish monthly journal under ISSN 2278-0181.

Online Version (e-copy)

<http://www.ijert.org>

Print Version

<http://www.ijert.org/for-authors/journal-print-version-download>

All the respective authors are the sole owner and responsible of published research and research papers are published after full consent of respective author or co-author(s). For any discussion on research subject or research matter, the reader should directly contact to undersigned authors.

COPYRIGHT

Copyright©2013, IJERT.ORG

All Rights Reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, scanning or otherwise, except as described below, without the permission in writing of the Publisher.

Copying of articles is not permitted except for personal and internal use, to the extent permitted by national copyright law, or under the terms of a license issued by the national Reproduction Rights Organization.

All the published research can be referenced by students / readers / scholars / researchers in their further research with proper citation given to original authors.

DISCLAIMER

Statements and opinions expressed in the published papers are those of the individual contributors, not the statements and opinion of IJERT. We assumes no responsibility or liability for any damage or injury to persons or property arising out of the use of any materials, instructions, methods or ideas contained herein. We expressly disclaim any implied warranties of merchantability or fitness for a particular purpose. If expert assistance is required, the services of a competent professional person should be sought.

Contact Information:

Email: editor@ijert.org

Website: <http://www.ijert.org>

Kiln-Dust as Partial Replacement of Cement in Concrete

Adakole Edwin Agbo¹, Calistus Ayegba²

1. Department of Building, Federal University of Technology Minna Niger State, Nigeria

2. Department of Building, Federal University of Technology Minna Niger State, Nigeria

Abstract

This research investigates the strength characteristics of concrete made with cement-kiln-dust with a view to determine the influence of replacing certain percentage of ordinary Portland cement with kiln-dust in cement kiln-dust concrete. The research was carried out in accordance with British standard BS (812, 882, 1881 and 4550). The kiln-dust was mechanically grounded into powder with grinding machine and sieved with a stack of BS sieve. The powdered kiln-dust was mixed with ordinary Portland cement in three different proportions of 10%, 20% and 30% content of kiln-dust which was used for experiment. Two hundred and forty 100mmX100mm concrete cubes were casted, cured and crushed including the controls specimens to failure to determine the compressive strength. The result of 28th day compressive strength for 10%, 20% and 30% replacement of OPC with kiln-dust were 27.5N/mm², 26.66N/mm² and 26.57N/mm² respectively. The water cement ratio for the mix proportion was 0.66, 0.75 and 0.87 for 10%, 20% and 30% replacement. The research concludes that OPC can be replaced with 10%, 20% and 30% of kiln-dust content in concrete.

Key words: Kiln-dust, Compressive strength, Concrete.

1. Introduction

Most developing countries like Nigeria have been suffering from an acute shortage of construction materials, principally because of the ever increasing demand for new construction works. The continuous demand for new construction works has triggered a continual increase in the cost of conventional building materials like cement.

The construction industry depends heavily on cementitious materials as binding agents in her operation to develop shelters and roads infrastructural works. Many cementitious materials has been used as binding agents in concrete, mortar and sandcrete

block but the most commonly used are cement and bitumen [2].

In Nigeria, cement is the generally used binder for construction works. Thus the demand for cement in Nigeria became higher than the supply and this has jacked up the price of cement beyond the level that an average income earner in Nigeria can afford [3]. This situation has necessitated the development of alternative and cheaper materials like kiln-dust, Rice-husk, Groundnut shell ash and other pozzolanas to mention a few to replace cement in concrete, mortar and sandcrete blocks [5 & 3].

The idea of using waste materials like Kiln-dust, rice-husk and groundnut shell ash as an alternative to cement have long been experimented. Apart from saving the cost of disposal, their use in construction protects the environment from pollution which could be harmful to human life [4 & 1]. Kiln-dust sometimes known as precipitator's dust is produced abundantly during the production process of ordinary Portland cement (OPC).

The dust is a waste product. Its chemical and physical composition varies from plant to plant. These variations are due to the variation in the raw materials used, location and types of collection used [1]. The behavior of the kiln-dust generally governed the choice of collection of the material for any construction work [1].

This research work was primarily informed as a result of forces of demand in the conventional cement which triggered the price of Portland cement in Nigeria beyond the reach of an average income earner in Nigeria. The knowledge of the practical usefulness of the kiln-dust will go a long way to benefit contractors, researchers as well as the society at large. However, the fundamental question to be ask here is, suppose local waste material like kiln-dust was used as a partial replacement of cement in concrete for construction, could it have performed

better than conventional cement in terms of strength, durability and cost wise?

This research is aimed at providing an answer to this question. The specific objectives of this research includes

1. To determine the physical and chemical composition of the kiln- dust
2. To determine the influence of kiln-dust on the strength characteristic of the cement kiln-dust concrete
3. To determine the required percentage content of ordinary Portland cement(OPC) that can be replace with kiln-dust in cement-kiln- dust concrete for high strength concrete.
4. To achieve these set objective, series of experiment where carried out as described in the next section.

2. Materials and Method

2.1 Material Collection

A number of materials were collected and used in the course of this study. The materials include: kiln-dust, fine aggregate (sand), coarse aggregate (crushed stone), ordinary Portland cement (OPC) and water. The kiln-dust was obtained from dangote cement in gboko, formal benue cement company (BCC). The fine and coarse aggregate were obtained from flooded pit and river in jos where the research was conducted.

2.2 Experimental Procedures

The experiment carried out for this research was grouped into two, the preliminary experiments and the main experiments.

2.2.1 Preliminary experiment

The quantity of the kiln-dust collected was grounded mechanically into powder from using grinding machine. The powder was sieved through a stack of BS sieve size 300µm, 150µm, and 75µm using mechanical sieve shaker to shake for 5 minutes. Only powdered particles that pass through the 75µm standard BS sieve (No 200) were collected and used for this experiment. The fine aggregate was natural sand from flooded pits which was of grading zone 1 of [7 & 8]. The coarse aggregate (crushed stone) was graded as satisfies [7] requirement for concrete graded coarse aggregate. Other preliminaries and tests carried out include: apparent specific gravity of the kiln-dust, bulk density test, water absorption test,

setting time test and chemical composition test as contained in the test result below.

2.2.2 Main/major experiment

For the purpose of this research, three mix proportions of cement-kiln-dust concrete with 10%, 20% and 30% content of powdered kiln-dust were used for the experiment. From the water absorption test, the appropriate water cement ratio was decided for each mix proportion.

The materials (gravel, sand, cement, kiln-dust and water) were mixed together manually between five to ten minutes (5-10 min) for each mix proportion and a uniform mix was achieved. Slump test for all the mix proportions were carried out according to [6]. A total of 240 cubes were casted for the three different mix proportions (10%, 20% and 30%) and for the control specimen. The specimens were cast in 100mm x 100mm steel cube moulds at ambient average room temperature of 32°C which is higher than recommended temperature of 21.11°C by the [13]. All the specimens in the cubes were compacted according to [9].

After 24 hours, the mould was removed from the specimens, and the specimens were cured in a curing tank using ordinary tap water in accordance with [8]. The curing was done for 7, 14, 21, 28, and 90 days. At the end of each curing period, 15 cubes for each mix proportion including the control mix will be removed from the curing tank and crushed manually to determine their compressive strength. Details of the results are shown on the next section.

Table 1.0 Quantity of materials in (kg) per cubic meter.

material	Control mix	10% replacement	20% replacement	30% replacement
	0% replacement			
Sand	8.365	8.365	8.365	8.365
Gravel	26.722	26.722	26.722	26.722
Water	0.705	0.911	0.930	0.971
Cement	1.253	1.127	1.002	0.876
Kiln-dust	0.00	0.125	0.251	0.377

3. Results and Discussion

This section presents the result of both preliminary test and the main test carried out in this research in a tabular form. The result of each the main test is presented in a separate table and discussed accordingly.

Table 2.1 Physical Properties of Materials.

Property	Kiln-dust	Sand (from flood pit)	Gravel	Cement
Apparent specific gravity	2.72	2.50	2.67	2.59
Sieve analysis	-	Zone 1	Size 20mm	-
Finness modulus	0.22	-	-	0.26
Loose bulk density	-	-	1337kg/m ³	-
Compacted bulk density	-	-	1413kg/m ³	-
Water absorption	40%	-	-	-
Initial setting time	1hr 38min	-	-	1hr 12mins
Final setting time	8hr 56min	-	-	4hrs 38mins

Table 2.2 Chemical composition

Kiln-dust	Percentage present	Cement	Percentage present
CaO	54.63	CaO	61.50
SiO ₂	17.84	SiO ₂	17.25
Al ₂ O ₃	5.14	Al ₂ O ₃	7.12
Fe ₂ O ₃	3.44	Fe ₂ O ₃	2.50
MgO	2.64	MgO	1.61
SO ₃	2.24	SO ₃	1.23
NaO	0.43	NaO	0.55
K ₂ O	0.38	K ₂ O	0.32
Loss in ignition	13.26		7.85

Source (field data) Soroka (1979)

The summary of the result in table 2a and 2b of the test carried out indicate compliance with standard of [7] for sieve analysis of fine and coarse aggregate. The specific gravity and water absorption satisfy [7 & 12]. The initial and final setting time of the kiln-dust was long but still within the stipulation of BS812. The bulk density (loose and compacted) of 1337kg/m³ and 1413kg/m³ indicate that the granite used for the experiment is of heavy weight since this values falls outside the value of 300 to 1200kg/m³ specified by [7] for light weight aggregate.

The chemical composition shows that the percentage of Cao, SiO₃ and Al₂O₃ present was up to 70% indicating the kiln-dust can be used as cementitious material to partially replace cement in construction works.

Table 3. Workability test

Kiln-dust content (%)	Slump (mm)	Compaction factor
10% replacement	45	0.93
20% replacement	43	0.92
30% replacement	38	0.92

The result of the slump test and compaction factors shown above on fresh concrete indicated concrete ranging from low to high workability. This result was within the specification of [6].

Table 4. Variations with Age of Compressive Strength

w/c ratio	OPC	%of OPC replaced with kiln dust	Compressive strength (N/mm ²)				
			7 days	14 days	21 days	28 days	90 days
0.45	Control mix	0	18.30	24.61	28.52	31.85	32.30
0.66		10	15.55	20.55	24.15	27.50	28.62
0.75		20	13.87	19.38	23.86	26.66	27.40
0.87		30	10.20	14.81	20.34	26.57	26.96

The result of compressive strength shown in table 4 reveals that at 28 days and 90 days of age, 0% (100% ordinary Portland cement) replacement gave the highest value of compressive strength of (30.85N/mm² and 31.0N/mm²) among all the mix proportions, but the strength decreases with an increase in the percentage of replacement by kiln-dust. For instance the 7th day's strength of 10% replacement with kiln-dust was 85% of the 0% replacement and the 28th day strength of 10% replacement with kiln-dust was 84% of 0% replacement. It was observed that in all the mix proportions, only the mix with 10% replacement attained 60% of its 28 day strength at 7 day. According to [13] concrete is expected to attain 60% of its 28 day compressive strength at 7 days. However, all the mix proportion (10%, 20% and 30% replacement) attained their expected compressive strength at 28 days. Similarly, there was a substantial difference between the 7th day and 28th day compressive strength for all the mix proportion. This was likely due to increase in hydration of the kiln-dust which normally occurs at a later age. This statement can be confirmed from the setting time period in table 29. With increase in age, more calcium hydroxide (a byproduct of ordinary Portland cement's hydration) is utilized by kiln-dust to produce more binding materials which will subsequently lead to more strength of the concrete [11]. It was also noticed that as the percentage of the ordinary Portland cement being replaced increases


(i.e. as the kiln-dust content increase) the 28th day and 90th day compressive strength of the concrete decreases. Though for concrete grade C25, C30 respectively for all the mix, it was observed that the highest strength obtained on 28th day was 27.50N/mm² which was from 10% replacement and the lowest was 26.27N/mm² which was from 30% replacement with kiln-dust. The rate of strength gain with age of the concrete is shown in table 6.

Table 6: Rate of Strength Gained with Age.

W/C ratio	OPC as control mix	% of OPC replaced with kiln-dust	Age (in days)				
			7	14	21	28	90
0.45	100% OPC	0	0	6.3	3.7	3.3	0.4
0.66		10	0	5.0	3.6	3.3	1.1
0.75		20	0	5.5	4.4	2.8	0.7
0.87		30	0	4.6	5.5	6.2	0.3

From the table 6 above, the control mix (100% OPC) and 10% replacement with kiln-dust indicate that the rate of strength gain decreases as the age of the concrete increases while 20% and 30% replacement with kiln-dust have no particular pattern.

Fig 1. Variation in Compressive Strength of Concrete with Age for the control mix and the entire % Replacement.



recommended that similar research should be carried out in mortar.

4. Conclusion

Based on the result of the test carried out on the compressive strength of the cement-kiln-dust concrete and the preliminary test carried out on the following conclusion were drawn

1. Ordinary Portland cement can be replaced with 10%, 20% and 30% with kiln-dust in concrete and still perform well as 0% replacement (100% cement).
2. The kiln-dust required high water cement ratio and longer period of setting time as compared to conventional OPC
3. The compressive strength of cement kiln-dust concrete decreases with increase in the percentage content of the kiln-dust
4. The highest compressive strength (28.62N/mm^2) was obtained from 10% replacement of OPC with kiln-dust at 90 days of age.

5. Recommendation

Based on the findings of this research work, it is recommended that further researches be carried out to establish the maximum percentage of OPC that can be replaced with kiln-dust in concrete. It is also

6. References

- [1]. Baghdadi, Z.A, Rhman, M.A (1990) Potential of Cement-Kiln-dust for stabilization of dun sand in highway construction. Building and Environment vol. 25, No4, pp284-289
- [2]. Neville, A.M, Brooks, J.J (2002) Concrete technology, 2nd edition Pearson Education Ltd New Delhi. Pp10-33, 356-375
- [3]. Dashan, I.I, Nwankwo, P.O (2000) The behavior of palm kernel shell concrete at elevated temperature. Nigerian Journal of Construction Technology and Management. vol3 No1 pp47-52.
- [4]. Ramakrishnan, V. (1986) "Evolution of kiln-dust in concrete" proceeding on fly ash, silica, fume slag and natural pozzolans in concrete. 2nd international conference, Madrid Spain. Vol. 1 pp821-839
- [5]. Job, F.O. (1998) Concrete made with Pulverized Burnt Clay as Partial Replacement of Cement. Nigerian Journal of Construction Technology and Management. vol 1 no1 pp29-33.
- [6]. British Standard Institution (1975, 1978) BS 812: Method of sampling and testing of materials/aggregate. British institution of London

[7]. British Standard Institution (1983) BS 882: Part 2: Aggregate from natural sources for concrete: British Standard Institution London
[8]. British standard institution (1983) BS 1881, part 3: method of normal curing of test specimen British standard institution London
[9]. British standard institution (1983) BS 1881, Part 102, 103 and 166: Methods of determine compressive strength, compaction factor and slump. British Standard Institution London.

[10]. British Standard Institution (1970) BS 4550: Part 2: Chemical test for cement. British Standard Institution London
[11]. Saad, M.M; Garba M.M; Okoli, O.G. (2007) comparative strength of pozzolana-portland cement mortar. Nigeria journal of construction technology and management vol. 8 No 1 pp 86-91
[12]. ASTM C 127-128. Test for finness of Portland cement by turbid meter.
[13]. Neville, A.M. (1981) properties of concrete 3rd Edn. London Pitman Publishing Company Ltd.

IJERT